

Rhenocryl 60 S Allgrund ME-AL, primer for metal, aluminum, mineral substrates

Rhenocoll Aqua-Premium Product
Art. No.: A 3331

Specification: primer.

For metallic substrates, such as iron, steel, aluminum, as well as mineral substrates, such as plaster, stone, cement compound materials. Contains corrosion protection and adhesion promoter for opaque follow-up coatings, such as for example Rhenocryl 90 S. Good covering power, 1-2 layer necessary, depending on substrate.

Processing: by brushing. Manual processing. For professional use only.

Features: in-can preservation

Supply form/color: white

Degree of gloss: satin-matt.

Substrate: mineral substrates, metal.

Further processing: several coats with Rhenocryl 90 S.
1- 2 layer are sufficient.

Consumption: approx. 75 – 100 ml/m² per coat

VOC: Cat. E / base wb / max value 130 g/L / actual value 16 g/L

Processing advice:

Processing consistency:	undiluted
Thinning:	with water
Cleaning of the tools:	with water or Rhenocoll Verdünner 140/1400 (thinner)
Processing temperature:	not below 8° C (material and room temperature)
Drying at normal climate:	depending on layer thickness, can be re-coated after 1 hr. Fully cured after several days.
Interior set-up:	1-2 coats, undiluted
Exterior set-up:	recommended are at least 2 coats, undiluted.
Storage:	cool, closed, in original container, for 1 year
General note:	Stir well before use and after longer breaks. Surface must be clean, dry and free from grease and wax.

Labeling: No labeling required.

Safety advice:

During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet.

Supply units:

750 ml tin
2,5 ltr pail
10 ltr pail

Service:

Our service team for application technology is available to you at any time without obligation.

Phone: +49 (0)6384 99 38 - 0
Fax: +49 (0)6384 99 38 - 112
Email: info@rhenocoll.de

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case.

With the release of this Technical Data Sheet all previous versions become obsolete