

# Technical Data Sheet

Rhenocoll Imprägnierung 30 S

Art.-No.: A 6050



Version: 2018/04, page 1 of 2


## Rhenocoll Imprägnierung 30 S, impregnation for wood

Art.-No.: A 6050

**Specification:** Impregnation, water-based, with excellent depth effect, for interior and exterior timber, balconies, façade paneling, cladding, pergola, building elements, windows and doors. With levelling effect for follow-up coats. Reduces the danger of staining. Odor-neutral.

**Application:** By brush, dipping, flow-coating.

**Preservation:** Our specific raw material selection makes the conventional equipment against bacteria, mold, fungi, and putrefactive agents unnecessary.

Self-immunizing	❖	Natural	❖	Mineral
<ul style="list-style-type: none"><li>✓ Designed for professional use</li><li>✓ No carcinogenic ingredients</li><li>✓ Free of Isothiazolones – free of microplastics</li><li>✓ Totally harmless to humans and animals</li><li>✓ Acts as an active protection of the environment, water, soil by conscious avoidance of toxic substances</li><li>✓ Protected by a worldwide patent</li></ul>				 <p>Protective shield the natural immunization</p>

**Supply form/color tone:** Available in colorless and translucent wood colors according to color chart: Design Collection 8 (Wood glaze).

**Substrate:** All soft- and hardwood

**Further treatment:** With Rhenocoll Imprägnierlasur or Compactlasur

**Consumption:** Approx. 120 - 160 ml/m<sup>2</sup>

**VOC:** Cat. E / base Wb / max. value 30g/L / actual value 19 g/L

**Ordinance on biocidal products:** Not subjected to registration, free from biocides

### Processing:

Processing consistency: Undiluted  
Viscosity: 10 – 11 seconds (flow cup 4mm).  
Thinning: With water  
Cleaning of tools: With water or Rhenocoll Verdünner 140/1400 (thinner).  
Cleaning of application units: Flush with water, post wash with solvents before longer periods of non-use (weekends).  
Processing temperature: Not below 8°C (material and room temperature).  
Drying time: at 20°C, 65-75% rel. humidity, depending on application strength, can be sanded after 30-120 minutes; further processing after 4 hours.  
Weather resistance: Rhenocoll Imprägnierung 30 S not recommended for exterior use on its own.

# Technical Data Sheet

Rhenocoll Imprägnierung 30 S

Art.-No.: A 6050



Version: 2018/04, page 2 of 2

General note: Stir well before use and after longer periods of non-use. Do not mix with solvent-based materials.

Flash point: None

**Labeling according to regulation (EG) No. 1272/2008:** No labeling required.

**ADR/GGVS:** Non dangerous goods.

**Safety Notes:** During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet. For professional use.

**Storage:** Store in the original container not below +8°C. Do not store or transport above +30°C for longer periods of time. Re-close firmly. Can be stored for 1 year in the unopened original container. Use product quickly, once container has been opened.

## Supply units:

750 ml tin

2.5 l pail

5 l pail

20 l pail

## Service:

Our service team for application technology is available to you at any time without obligation.

**Phone:** ++49 (0)6384 99 38 - 0

**Fax:** ++49 (0)6384 99 38 - 112

**Email:** [info@rhenocoll.de](mailto:info@rhenocoll.de)

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case. With the release of this Technical Data Sheet all previous versions become obsolete.