

Technical Data Sheet

Rhenocryl IL 48 (K)

Art.No.: A 3316



version: 20012/08, page 1 of 2

Rhenocryl IL 48 (K), insulating sealer

Rhenocoll Aqua **Klassik** industrial product

Art. No.: A 3316

Specifications: Intermediate coating with special insulating properties against a bleeding of the ingredients contained within the wood; water-based; based on special resins; for wood in exterior areas, building elements, windows and doors. Very high layer building ability due to high solids content. Ecologically friendly. Of neutral odor. Reduces moisture fluctuations. Excellent sanding properties thanks to its high solids content.

Application: by spraying or by brush. For professional use.

Features: In-can preservation.

Supply form/color: White, opaque.

Substrate: All soft and hard wood.

Pre-treatment: Impregnation or primer.

Further processing: Film-building paint (water-based), top coat and special coating systems, such as the Rhenocoll Klassik coating system for building elements; for an opaque top coat.

Consumption: In order to obtain a sealing effect, up to 200 ml/m² are necessary (depending on the type of wood).

VOC directives 2010:

Cat. D / base wb / max value 130g/l / actual value 45 g/l

Processing instructions:

Processing: undiluted
Airmix spraying system
(0,28-0,33 mm nozzle, pistol filter 100-180 meshes)

Viscosity: 2700 – 3000 mPas

Layer strengths: max. 200 µ wet film

Thinning: with water

Cleaning of the tools: with water or thinner 140 / 1400.

Cleaning of the machine: flush with water; before longer breaks (weekend) clean again with Phasenumwandler VP 724.

Processing temperature: above 8°C (material and room temperature)

Drying at normal climate: at 20°C, 65-75% relative humidity depending on the thickness of the coat, can be sanded after 1-3 hrs; with forced drying (40°C) after 1-2 hrs and at below 15°C after up to 6 hrs to be processed further.

Setting time: In order for the sealing effect to develop, setting times are to be observed, depending on the type of wood and wood ingredients. Although the coat could be sanded after 90 min, a setting time of 24 hrs would have to be observed in extreme cases.

Technical Data Sheet

Rhenocryl IL 48 (K)

Art.No.: A 3316



version: 20012/08, page 2 of 2

Weather resistance:	Rhenocryl IL 48 K is not recommended as the only coating for exterior use.
Wood moisture content:	10-12%.
Storage:	Cool and frost-free. Can be stored in original container for one year.
General:	Stir before use and after longer breaks; do not mix with solvent-based products or other water-based products.
Flash point:	none

Coating system: For timber windows and exterior doors out of soft and hardwood.

Preparation: Dust wooden parts thoroughly. Wash resinous and sticky surfaces with universal thinner. In order to avoid problems with blocking glass batten must not remain in the frame. Coating systems according to the chart "Coating systems for windows and exterior doors" published by the German Institute for Window Technology e.V. (IFT), edition 5.83.

Labeling:

No labeling

Safety advice:

During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet.

Supply units:

750 ml tin
2.5 l pail
5 l pail
25 l hobbock
150 l barrel

Service:

Our service team for application technology is available to you at any time without obligation.

Phone: ++49 (0)6384 99 38 - 0

Fax: ++49 (0)6384 99 38 - 112

Email: info@rhenocoll.de

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case.

With the release of this Technical Data Sheet all previous versions become obsolete.