

**Rhenocoll Para Skin 02, liquid protective film, colorless**  
**Art.-No.: A 3756**

**Specification:** Protective film for painted smooth surfaces, water-based, colorless. The fast drying, pasty protective varnish is applied as a liquid film which forms a solid film. Especially suitable to coat surfaces which had been painted. After drying the particularly elastic film can be peeled off in big pieces.

**Application:** Processing undiluted, with a roll, brush or by spraying (cub gun), applicable in common processing temperatures. Free of solvents, can therefore also be used in Ex-protected areas. Operating values of the cub gun: nozzle 2,2 mm / pressure 2,5 bar. For professional use.

**Drying:**

Rhenocoll Para Skin 02 dries at room temperature as well as increased temperature.

Layer thickness 200 µ, drying time approx. 45 - 60 min. (at 20°C)

Layer thickness 400 µ, drying time approx. 60 - 120 min. (at 20°C)

Layer thickness 400 µ, drying time approx. 10 - 30 min. (at 40°C)

**Storage:** Cool and firmly closed in original containers. Can be stored for 1 year.

**Application amount:** 4 - 6 m<sup>2</sup> / kg, stir well before use.

**Labeling according to regulation (EC) No 1272/2008:**

CAUTION

**GGVS/ADR:** Non dangerous goods

**VOC directives 2010:** Cat. I / base Wb / max value 140g/L / actual value 0g/L

**Safety advice:** During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet.

**Supply units:**

1 kg tin

6 kg pail

21 kg pail

**Service:**

Our service team for application technology is available to you at any time without obligation.

**Phone:** ++49 (0)6384 99 38 - 0

**Fax:** ++49 (0)6384 99 38 - 112

**Email:** [info@rhenocoll.de](mailto:info@rhenocoll.de)

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case. With the release of this Technical Data Sheet all previous versions become obsolete.