

Tec-Bond-Promotor 05 (VP.6389)

Art. No.: A 4605

Adhesion promoter for AQUA Glaslack

Application area: Tec-Bond-Promotor 05 is a special additive for Rhenocoll AQUA Glaslack G5 for the improvement of the adhesion onto glass. For professional use.

Processing instructions: Stir or shake AQUA Glaslack well before use. Tec-Bond-Promotor 05 does not need to be stirred. Add promoter to the varnish and stir well. The mixture should be passed through a filter bag to guarantee the best results. If the mixture is not stirred sufficiently specks may develop, which can be filtered. Please use filter bag 40µ (art. no. A8233). Aqua-Glaslack is now ready to use.

Addition of promoter: Add at a quantity of 5% promoter to the varnish (1 liter varnish + 50 ml promoter). Mix manually.

Pot life after mixing with promoter: Within one working day (8-12 hours). After this time, the mix can be used in the follow up coats, but not directly onto glass anymore. A change in viscosity is possible after a few days.

Cleaning: With water, immediately after use. Dried residue can be cleaned with Rhenocoll Verdünner 140/1400 (thinner) or acetone.

Storage: Tec-Bond-Promotor 05 can be stored for 6 months in the unopened original container. After opening use within 3 months.

Supply units:

50 ml Bottle (Sufficient for 1 Liter varnish)
100 ml Bottle (Sufficient for 2 Liter varnish)
500 ml Bottle (Sufficient for 10 Liter varnish)
5 ltr. Canister (Sufficient for 100 Liter varnish)

VOC 2010: n/a

Labeling according to regulation (EC) No 1272/2008: DANGER - H318

GGVS/ADR: Non dangerous goods

Safety advice: During processing, common protection measures and regulations according to the authorized trade association must be observed. Safety-relevant data and instructions regarding disposal can be found in the safety data sheet.

Service:

Our service team for application technology is available to you at any time without obligation.

Phone: ++49 (0)6384 99 38 - 0

Fax: ++49 (0)6384 99 38 - 112

Email: info@rhenocoll.de

The information given within is without obligation and is based on practical experience as well as on experiments which we have carried out and are not attribute guaranties in the sense of the newest BGH legal requirements. We recommend that in any case users carry out their own tests since we have no influence over the large diversity of materials and their processing. No liability for the manufacturer can be derived from the contents of this data sheet. Statements going beyond or deviating from the contents of this data sheet require the written confirmation of the company headquarters. Our General Terms & Conditions apply in any case. With the release of this Technical Data Sheet all previous versions become obsolete.